



Description

723 UL is a **UL 723** classified product cast on a paper liner. Product is UL listed from 1/16" to 1/4" in thickness with an acrylic PSA.

Applications

723 UL is used in any application requiring a UL 723 rating where an aluminum liner is not required or desirable. 723 UL remains pliable between -20°C to 78°C.

Storage

Product shelf life begins on the date of production as referenced by the lot number. Foam Seal 723 UL has a minimum shelf life of 6 months when stored at or below 75°F.

Additional Information

Foam Seal believes that the information provided is a true and accurate description of the typical characteristics of the aforementioned product; however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy and safety.

Product Specifications

Parameter	Test Method	Size Range / Condition	Specification
Gage (Thickness)		1/8" - < 3/16" 3/16" - 1/4"	+ - 15 % + - 10 %
Width (Rolls)		3/16" - < 2" wide 2" - 50" wide	+ - 1/32" + - 1/16"
Length		=< 50' long > 50' long	- 0" + 6" - 1 % + 2 %
Density (lbs/cu ft)	ASTM D-1667		6.0 - 9.0
Adhesion	ASTM D-1000	Stainless steel	12 oz / in min

Specifications based on a sample size of three to five. Testing to these specifications may be dependent on the specific application. Specifications are subject to change without notice.

Information for Reference Only

Parameter	Test Method	Typical Values
Water Absorption	ASTM D-1056	3%
Hardness "00"	ASTM D-2240	30
Force to Compress psi @ 25%	ASTM D-1667	3.0
Compression/ Deflection 25% after 60 sec	ASTM D-1667	2.0

The information provided in the above table is not intended for use in preparing specifications. Information for reference is intended as a general guideline only. Typical values based on a sample size of three to five

UL 723 File # R20969

Parameter	Flame Spread	Smoke Index
PVC Foam Core	20	100
Foil Faced Foam (slit)	15	45