

NOVAGARD[®]

SILICONES

Novaflex[®] M164

Specification Data

DESCRIPTION

Novaflex M164 is a non-corrosive, single-component, oxime cured silicone sealant. A non-flowable, paste product, M164 cures to a solid rubber with many of the same characteristics as any normal silicone RTV except that it has low adhesion. Lower odor than conventional acetoxy cured silicones.

APPLICATIONS

M164 is a general-purpose, multi-functional compound, which is used most frequently within the window and door manufacturing industry. M164 is a single-component, high-solids, low-odor material, which cures to a low modulus, flexible and durable rubber-like solid. M164 develops extremely low adhesion to most common construction substrates, and the neutral cure is compatible with most materials.

INSTALLATION

As with all single component materials, worklife and cure times of M164 are dependent upon environmental conditions such as temperature, humidity and application thickness. Adhesion should be checked on small samples prior to full-scale production.

STORAGE

Novaflex M164 has a shelf life of eighteen (18) months from the date of manufacture when stored in the original, unopened container at, or below, 75°F.

PRODUCT SPECIFICATIONS

Physical Property	Test Method	Performance Range
Appearance		Translucent paste
Viscosity	Brookfield #7 @ 10rpm	3500 - 7000 poises
Skin Over Time	3/8" @ 50%RH & 77F	10-15 minutes
Through Cure	3/8" @ 50%RH & 77F	24 hours

PRECAUTIONS

Consult and obey all applicable local, state and federal regulations for disposal of solvent and silicone waste. For additional information consult product M.S.D.S.

Do not use in or around highly oxidative chemicals such as liquid oxygen, chlorine or peroxides. Not recommended for surfaces that are to be painted.

AVAILABILITY

Novaflex[®] M164 is available in 10.3 oz. cartridges, 5-gallon pails, and 55-gallon drums.

ADDITIONAL INFORMATION

Novagard believes that the information provided is a true and accurate description of the typical characteristics of the aforementioned product; however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy and safety.

TYPICAL PROPERTIES*

Physical Property	Test Method	Typical Value
Specific Gravity		1.00 – 1.05
Tensile Strength	ASTM D412	140-180 psi
Elongation	ASTM D412	500-600%
Tear Resistance	ASTM D 624	30-35 pli
Shore Hardness	ASTM D 2240	20 ± 5

*The values outlined reflect testing that was conducted on laboratory prepared specimens, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.

Novagard **Solutions**[™]
5109 Hamilton Avenue
Cleveland, OH 44114
Phone: (216) 881-3890 Facsimile: (216) 881-6977
WWW.NOVAGARD.COM

Form Name
10-D2-MX164

Phone: (216) 881-3890 Facsimile: (216) 881-6977

Effective Date
04-01-08