

Novagard® RTV 400-155

Specification Data



DESCRIPTION

Novagard RTV 400-155 is a high strength, one-part adhesive designed for rapid green strength and excellent adhesion to a wide variety of substrates.

APPLICATIONS

Specially formulated to retain its physical properties even during service in extreme environmental conditions, Novagard RTV 400-155 is a smooth, translucent paste that is ideal for applications that require superior bond strength and moisture resistance. Novagard RTV 400-155 is well suited to perform within many arenas.

INSTALLATION

As with all single component materials, work life and cure times of Novagard RTV 400-155 are dependent upon environmental conditions such as temperature, humidity, and application thickness. Adhesion should be checked on small samples prior to full-scale production.

AVAILABILITY

Standard packaging is 10.3 oz cartridges. Many other packaging options are available with minimum purchase amounts. Call your Novagard representative or customer service for inquiries.

STORAGE

Novagard RTV 400-155 may be stored in the original unopened container at, or below, 80°F for up to one year.

PRECAUTIONS

Consult and obey all applicable local, state, and federal regulations for disposal of solvent and silicone waste. For additional information consult product S.D.S.

Do not use in or around highly oxidative chemicals such as liquid oxygen, chlorine, or peroxides. Not recommended for surfaces that are to be painted.

PRODUCT SPECIFICATIONS

Physical Property	Test Method	Performance Range
Appearance		Translucent Paste
Extrusion Rate	1/8" nozzle @ 50 psi	40 gm/minute minimum
Skin Time	3/8" @ 50% RH & 77°F	5 - 15 minutes
Through Cure	1/8" @ 50% RH & 77°F	3 - 6 hours
Tensile Strength	ASTM D412	200 psi minimum
Elongation	ASTM D412	300% minimum

TYPICAL PROPERTIES*

Physical Property	Test Method	Typical Value
Specific Gravity		1.00 – 1.05
Shore Hardness	ASTM D2240	20 - 40
Adhesion		
Glass	ASTM D903	20 pli minimum
Wood	7 Days @ 75°F/50% RH	20 pli minimum
Aluminum		20 pli minimum

*The values outlined reflect testing that was conducted under laboratory conditions, actual results may vary. The information provided in the above table is not intended for use in preparing specifications. Please consult manufacturer for additional information.

ADDITIONAL INFORMATION

Novagard believes that the information provided is a true and accurate description of the typical characteristics of the aforementioned product, however, it is the responsibility of the individual user to thoroughly test the product in their specific application to determine performance, efficacy, and safety.